

P009

Perforated Acoustic Absorption Panel

WOODFIT
ACOUSTICS


.80

Noise Reduction Coefficient (NRC)

4.47%

Open Area


www.woodfitacoustics.com



Sound Absorption

— Installation A : 50mm rockwool insulation


— Installation B : 50mm rockwool insulation plus 200mm cavity




Frequency	125	250	500	1K	2k	4k
Installation A	0.32	0.65	0.89	0.85	0.79	0.61
Installation B	0.31	0.84	0.92	0.87	0.65	0.51

Materials & Colours


Veneer/ Melamine/ Laminate




WHITE OAK




MAPLE




CHERRY



WALNUT



ASH



LIMED OAK



Available Dimensions: 600mm x 600mm, 1200mm x 600mm, custom

Available on Request:

- Fire rating Euroclass B/C/D
- FSC certification
- Custom cutouts, size, shape, curvature

Available on Request:

- Large range of veneers, laminates and melamines
- RAL colour lacquer and colour board

Please Note

- All colours and grains subject to availability
- Wood is a natural material and may be subject to shade variations

